

# GTS-PP-65

# **3LPP Hybrid Coating System**

The GTS-PP-65 system is a hybrid system combining a Polypropylene backing with a mastic adhesive. This combination results in a product with the mechanical protection of polypropylene with the ease of installation of a traditional adhesive. This also allows for a lower preheat temperature and faster application then found with traditional 3LPP systems.

#### **Superior Mechanical Protection**

 The GTS-PP-65 sleeve has superior impact and shear resistance by virtue of its polypropylene backing. The sleeve is engineered for use in offshore applications where mechanical resistance is required and the rapid cooling of polypropylene allows better resistance to offshore laying rollers.

### **Unique Adhesive Technology**

- Allows for lower installation pre-heat temperatures and superior bonding to PP, PE, FBE, AE and CTE coatings.
- The adhesive has been formulated to bond directly to the steel and mainline coating.

## Flexible installation

 For added flexibility, the sleeve can be supplied as either pre-cut to the required pipe sizes or as bulk rolls.

## **Long Term Corrosion Protection**

Provides a protective coating with the structural integrity
of a seamless tube, providing excellent resistance to cathodic
disbondment and excellent durability against abrasion and
chemical attack.

#### **Saves time and Money**

- Lower pre-heat means less time heating and a faster installation.
- Excellent quenching properties allow for faster cycle times during offshore installations.



## **Applications**



Oil & Gas



Offshore, J & S Lay



High Abrasion Environments



High Moisture Environments



# GTS-PP-65

# **3LPP Hybrid Coating System**

Sleeve Operating Characteristics	Test Method		Typical Values
Offshore Pipeline Operating Temp.			Up to 65°C (149°F)*
Minimum Installation Temp.			75°C (167°F)
Rapid Quenching Ability			Excellent
Main Line Coating Compatibility		Р	E, PP, FBE, AE & CTE
Adhesive Properties			
Softening Point	ASTM E28		102°C
Lap Shear @ 23°C	EN 12068		15 N/cm <sup>2</sup>
Backing Properties			
Tensile Strength	ASTM D638		28 MPa
Elongation	ASTM D638		425%
Hardness	ASTM D2240		65 Shore D
Volume Resistivity	ASTM D257		2 x 10 <sup>17</sup> ohm-cm
Sleeve Properties			
Adhesion Strength @ 23°C	EN 12068		15 N/cm
Impact Resistance	EN 12068		> 20 J
Indentation Resistance	EN 12068		Pass
Cathodic Disbondment @ 23°C, 28 days	ASTM G8		< 8 mm rad
Bending Resistance	GBE/CW6		Pass
Thickness	Т	L	S
Backing (nominal thickness as supplied)	0.9 mm (0.035")	0.9 mm (0.035")	1.1 mm (0.045")
Adhesive (nominal thickness as supplied)	0.9 mm (0.035")	1.4 mm (0.055")	1.5 mm (0.060")

<sup>\*</sup> Actual temperature rating is dependant on specific project requirements and conditions. Please consult your local Canusa representative.

Since 1967, Canusa-CPS has been a leading developer and manufacturer of specialty pipeline coatings for the sealing and corrosion protection of pipeline joints and other substrates. Canusa-CPS high performance products are manufactured to the highest quality standards and are available in a number of configurations to accommodate many specific project applications.

The product information shown here is intended as a guide for standard products.

Consult your Canusa representative for specific projects or unique applications at info@canusacps.com.



### Western Hemisphere

SFL Canusa - WH 4757 93rd Ave NW Edmonton, Alberta T6B 2T6 Canada

Tel: +1587-754-8701

#### Еигоре

SealForLife Industries Nijverheidsstraat 13 B-2260 Westerlo Belgium

#### Middle East

SFL Canusa Middle East PPTS LLC KLP5, Block B, Unit B-01, Sector no.: KHIA8, Al Ma'mourah PO Box 2621, Abu Dhabi, The United Arab Emirates

Quality Management system registered to ISO 9001

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the product data sheet when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this data sheet is to be used as a guide and is subject to change without notice. This data sheet supersedes all previous data sheets on this product. E&OE

PDS\_GTSPP65\_rev017

