

PLA

Tubular sleeve for pipeline corrosion protection

The PLA is a heat shrinkable tubular sleeve designed for corrosion protection of buried and exposed steel pipelines. PLA consists of a crosslinked polyolefin backing, coated with a protective heat sensitive adhesive which effectively bonds to steel substrates and common pipeline coatings including polyethylene and fusion bonded epoxy.

Rapid & Reliable Installation

- PLA consists of a unique tubular configuration that has been factory constructed, resulting in a quick and reliable field installation.
- PLA is manufactured with a specially formulated adhesive to accommodate demanding operating temperatures and soil stress conditions.

Long Term Corrosion Protection

- PLA provides excellent resistance to cathodic disbondment resulting in effective long term corrosion protection.
- The high performance crosslinked backing in combination with the specially formulated adhesive is engineered to have excellent resistance against temperature cycling, and chemical and environmental attack.

Saves Time & Money

- With PLA's unique construction, less time is required handling, positioning and installing separate closures.
- This feature allows for a fast, simple and complete installation of the sleeve, with no primers required. This minimizes installation time and labour costs while promoting high production rates.



Applications



Oil & Gas



Water Pipelines



Utility Poles



Sleeve Operating Characteristics		Test Method	Typical Values
Pipeline Operating Temp.			Up to 55°C (131°F)*
Minimum Installation Temp.			60°C (140°F)
Mainline Coating Compatibility			PE, FBE
Adhesive Properties			
Softening Point		ASTM E28	81°C
Lap Shear @ 23°C		ISO 21809-3	> 90 N/cm ²
Lap Shear @ 50°C		ISO 21809-3	> 5 N/cm ²
Backing Properties			
Tensile Strength		ASTM D638	20 MPa
Elongation		ASTM D638	600%
Hardness		ASTM D2240	46 Shore D
Volume Resistivity		ASTM D257	10 ¹⁷ ohm-cm
Sleeve Properties			
Adhesion Strength @ 23°C		ISO 21809-3	> 30 N/cm
Adhesion Strength @ 50°C		ISO 21809-3	> 9 N/cm
Impact Resistance		ISO 21809-3	Pass
Indentation Resistance		ISO 21809-3	Pass
Cathodic Disbondment @ 23°C, 28 days		ISO 21809-3	< 13 mm rad
Low Temp. Flexibility		ASTM D2671-C	-25°C
Thickness			
Backing (nominal thickness as supplied)			0.6 mm (0.025")
Adhesive (nominal thickness as supplied)			0.9 mm (0.035")

* Actual temperature rating is dependant on specific project requirements and conditions. Please consult your local Canusa representative.

Product Selection Guide


Choose your sleeve based on your pipe diameter.

Nominal Pipe Diameter	Outside Pipe Diameter	Tubular Sleeve		Tubular Sleeve Diameter				
		PLA-XXX-YYY ZZ	As Supplied	Fully Recovered				
DN 50	2"	61 mm	2.4"	PLA-55-YYY ZZ	90 mm	3.5"	55 mm	2.3"
DN 65	2.5"	76 mm	3"	PLA-63-YYY ZZ	90 mm	3.5"	63 mm	2.5"
DN 80	3"	89 mm	3.5"	PLA-90-YYY ZZ	120 mm	4.8"	81 mm	3.3"
DN 90	3.5"	102 mm	4"	PLA-100-YYY ZZ	130 mm	5"	90 mm	3.5"
DN 100	4"	114 mm	4.5"	PLA-115-YYY ZZ	145 mm	5.5"	98 mm	3.8"
DN 125	5"	141 mm	5.5"	PLA-125-YYY ZZ	160 mm	6.3"	110 mm	4.3"
DN 150	6"	168 mm	6.6"	PLA-170-YYY ZZ	205 mm	8"	140 mm	5.5"
DN 200	8"	219 mm	8.6"	PLA-230-YYY ZZ	260 mm	10"	180 mm	7"
DN 250	10"	273 mm	10.7"	PLA-280-YYY ZZ	315 mm	12.3"	211 mm	8.3"
DN 300	12"	324 mm	12.8"	PLA-315-YYY ZZ	360 mm	14"	245 mm	9.5"

For pipe diameters > DN 300 (12"), consult your Canusa representative.

How to Order

PLA 115-450 BK		Standard Ordering Options	
Color		BK - Black	
Sleeve Width		300 mm, 450 mm, 600 mm, 900mm (12", 18", 24", 36")	
Pipe Size		55 mm - 315 mm (2" - 12")	
Configuration		Product Name	



Min. Sleeve Width = Bare Steel Dimension + 50 mm (2") min. on each side of the pipe joint.

The above represents standard ordering options. Consult your Canusa-CPS representative for any unique project requirements.

Since 1967, Canusa-CPS has been a leading developer and manufacturer of specialty pipeline coatings for the sealing and corrosion protection of pipeline joints and other substrates. Canusa-CPS high performance products are manufactured to the highest quality standards and are available in a number of configurations to accommodate many specific project applications.

The product information shown here is intended as a guide for standard products.

Consult your Canusa representative for specific projects or unique applications at info@canusacps.com.



Western Hemisphere

SFL Canusa - WH
4757 93rd Ave NW
Edmonton, Alberta T6B 2T6
Canada

Tel: +1 587-754-8701

Europe

SealForLife Industries
Nijverheidsstraat 13
B-2260 Westerlo
Belgium

Middle East

SFL Canusa Middle East PPTS LLC
KLP5, Block B, Unit B-01,
Sector no.: KHIA8, Al Ma'mourah
PO Box 2621, Abu Dhabi,
The United Arab Emirates

Quality Management
system registered to
ISO 9001

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the product data sheet when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this data sheet is to be used as a guide and is subject to change without notice. This data sheet supersedes all previous data sheets on this product. E&OE

PDS_CanusaTube PLA_rev016